

PRODUCT SPECIFICATION

Technical Sheet: FSO-50/55 RESIN

DESCRIPTION

Solid Phenolic-Novolac resin for hot sand covering.

PROPERTIES

•	Appearance	Solid yellow color
---	------------	--------------------

•	DMP (ºF) 250 – 260 °F

• % Free Phenol Max.2%

• Viscosity (150°C, cps) Max. 2500

PRESENTATION

Solid in flakes packaged in bulk bags of 1,616 lbs. The flakes of the resin have the following dimensions:

• Length and width: from $^3/_{32}$ to $^1/_2$ inches

• Thickness: $^3/_{32}$ to $^5/_{32}$ inches

STORAGE

Storage in fresh, dry and clean space with a temperature < 30° kept away from heat sources and acid materials. Avoid humidity exposure.